



**DIVERSIFIED**  
TESTING LABORATORIES, INC.  
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET  
P.O. BOX 4004  
BURLINGTON, NORTH CAROLINA 27215  
PHONE (336) 227-7710 • FAX (336) 227-1175  
www.diversifiedtestinglabs.com

October 9, 2023

Fire Velvet BA9-xxx  
available in 16 colors

Mr. Jacob Visoky  
LIBA FABRICS CORP.  
132 West 36<sup>th</sup> Street, 6<sup>th</sup> Floor  
New York, NY 10018

Reference: Laboratory Test Report  
Lab Identification No. 56987  
Invoice No. 88268

Dear Mr. Visoky:

One (1) fabric sample, identified as **2020 – IFR Fire Velvet – 100% Polyester**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2023 Edition, (Test 1)". The results are as follows:

**Test Results**

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	16.97
2	0.0	10.60
3	0.0	20.68
4	0.0	15.00
5	0.0	18.36
6	0.0	8.18
7	0.0	9.86
8	0.0	9.03
9	0.0	13.97
<u>10</u>	<u>0.0</u>	<u>9.78</u>
<b>AVG</b>	<b>0.0</b>	<b>13.24</b>

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

